



DATA SHEET

ITEM No	Ceramic Fiber Bulk-STD	
Physical Property:		
Classification Temperature ℃	*	1260
Working Temperature℃	*	1050
Short Content %	*	<15
Color	*	White
Chemical Analysis(%)		
Al2O3	*	45-47
Al2O3+SiO2	*	98.5
Fe2O3	≦	0.4
Na2O+K2O	≦	0.3
CaO+MgO	≦	0.2
Note:All data are average values obtained at samples for laboratory purposes.		

Henan Ruitai Refractory Materials Technology Co.,Ltd

ADD: 15 km away from Zhengzhou International Airport,

Zhengzhou 451100, Henan, China

Tel: 0086-371-62586888 Fax: 0086-671-62585779

Website: www.ruitairefractories.com Email: ruitairefractories@163.com



DATA SHEET

ITEM No	Ceramic Fiber Bulk-HP	
Physical Property:		
Classification Temperature ℃	*	1260
Working Temperature℃	*	1100
Short Content %	*	<15
Color	*	White
Chemical Analysis(%)		
Al2O3	*	45-46
Al2O3+SiO2	*	99
Fe2O3	≦	0.3
Na2O+K2O	≦	0.3
CaO+MgO	≦	*
Note:All data are average values obtained at samples for laboratory purposes.		

Henan Ruitai Refractory Materials Technology Co.,Ltd

ADD: 15 km away from Zhengzhou International Airport,
Zhengzhou 451100, Henan, China

Tel: 0086-371-62586888 Fax: 0086-671-62585779

Website: www.ruitairefractories.com Email: ruitairefractories@163.com



DATA SHEET

ITEM No	Ceramic Fiber Bulk-HA	
Physical Property:		
Classification Temperature ℃	*	1350
Working Temperature℃	*	1200
Short Content %	*	<15
Color	*	White
Chemical Analysis(%)		
Al2O3	*	53-55
Al2O3+SiO2	*	99
Fe2O3	≦	0.2
Na2O+K2O	≦	0.2
CaO+MgO	≦	0.2
Note:All data are average values obtained at samples for laboratory purposes.		

Henan Ruitai Refractory Materials Technology Co.,Ltd

ADD: 15 km away from Zhengzhou International Airport,
Zhengzhou 451100, Henan, China

Tel: 0086-371-62586888 Fax: 0086-671-62585779

Website: www.ruitairefractories.com Email: ruitairefractories@163.com



DATA SHET

ITEM No	Ceramic Fiber Bulk-HZ	
Physical Property:		
Classification Temperature ℃	*	1430
Working Temperature℃	*	1350
Short Content %	*	<15
Color	*	White
Chemical Analysis(%)		
Al2O3	*	38-54
Al2O3+SiO2	*	82-90
Fe2O3	≤	0.2
ZrO2	*	10-18
Na2O+K2O	≤	0.2
CaO+MgO	≤	0.2
Note:All data are average values obtained at samples for laboratory purposes.		

Henan Ruitai Refractory Materials Technology Co.,Ltd

ADD:15 km away from Zhengzhou International Airport,

Zhengzhou 451100,Henan, China

Tel:0086-371-62586888 Fax:0086-671-62585779

Website: www.ruitairefractories.com Email: ruitairefractories@163.com