



DATA SHEET

Innovative High Temperature Refractory Mortar			
Physical Property:			
Modules of Rupture(MPa)	110℃*24H	≥	5
	1100℃*3H	≥	6
	1350℃*3H	≥	10
Refractoriness(℃)		≥	1800
Chemical Analysis(%)			
MgO		≥	50
Note:All data are typical values			

Henan Ruitai Refractory Materials Technology Co.,Ltd

ADD:26km away from Zhengzhou International Airport,
Zhengzhou 451100,Henan, China

Tel:0086-371-62586888 Fax:0086-671-62585779

Website: www.ruitairefractories.com Email: ruitairefractories@163.com